



TENERIAS OMEGA, S.A.

Ctra. Estella-Tafalla, km 2,3
31132 VILLATUERTA-Navarra-Spain
Telf. +34-948-546051
Fax +34-948-546144
www.teneriasomega.com



RENO

Our Train product line was developed specifically to meet the needs of rail system operators with respect to design, maintenance and standards compliance.

Fulfills the requirements of EN 45545-2, R21, with HL 1-3. This result is based on preliminary tests.

Train leather is produced from European raw hides in substance 1.1-1.3mm. Average hide size 50 sqft.

TECHNICAL PROPERTIES

<u>PROPERTY</u>	<u>MINIMUM VALUE</u>	<u>METHOD</u>
Thickness	1-1.3 mm	DIN 53326
Flexometer	100.000 Flexes	DIN EN 13334
Wet-Rubbing	200 cycles - 5	DIN EN ISO 11640
Dry-Rubbing	1.000 cycles - 5	DIN EN ISO 11640
Light Fastness	5	ISO 105-B02
Tear-Strength	25 N	DIN 53329
Abrasion (Taber Test)	2000 cycles	DIN 53109 CS-10 wheels, 500 g. weight

FIREPROOF CHARACTERISTICS

- Flammability: FAR 25853 Part. I
- Smoke density: AIRBUS ABD0031, BOEING BSS 7238
- Toxicity of gasses: AIRBUS ABD0031, BOEING BSS 7239

Other Technical or legal Requirements to which we comply.

- In accordance to the limited values of PCP, Chrome VI, aromatic amines indicated in the European regulation 2002/61/CE
- In accordance with the European regulation 2006/139/CE
- According to the European Regulation 2000/53/CE
- According to the European regulation 1907/ 2006 (REACH)